

HYPERDESMO® -S

New Generation, Low Solvent, Thixotropic, Polyurethane liquid membrane for waterproofing and protection.

DESCRIPTION

HYPERDESMO®-S is a result of Alchimica's investment in new production facilities and polymerization procedures. This investment facilitated the manufacture of a low solvent **Hyperdesmo®** i.e a non-flammable material without hazardous transportation limitations (non-imo). Furthermore, with **HYPERDESMO®-S** waterproofing of complex structures, vertical substrates is now easily done even in one coat as rheology such that it allows easy application of this kind and the product displays minimum bubble formation even in high consumptions.

The use of all Hyperdesmo® range additives is possible: Accelerator 3000, Thixo Tool, Solvent 01 and Alchimica pigment pastes.

Full range of Primers used in classic Hyperdesmo system applies to HYPERDESMO®-S as well.

Apply with brush, roller or airless spraying in two coats with minimum total consumption of 1.5 kg/m².

RECOMMENDED FOR

Waterproofing of:

- Complex structures(excellent rheology)
- Roof tiles, flat roofs where CE marking is not a pre-requisite (in such cases refer to Hyperdesmo®)
- walls
- Protection of PU foam
- verandas and balconies
- wet rooms
- Planters boxes

LIMITATIONS

Not recommended for:

- Unsound substrates,
- waterproofing of swimming pool surfaces in contact with chemically treated water.



When used in dark colours for exposed use, a protective topcoat of HYPERDESMO®-ADY-E (always pigmented) is required

FEATURES & BENEFITS

- Highly Elastic
- Easy application even on vertical substrates
- Resistance to cold: The film remains elastic even down to -40 °C.
- Low solvent, non-Flammable
- Non-toxic after full cure.
- Water vapor transmission: The film breathes so there is no accumulation of humidity under the coat.
- Special primers available for almost any substrate.

APPLICATION PREREQUISITES

Can be successfully applied on:

Concrete, fibrous cement, mosaic, cement roof tiles, old (but well adhered) acrylic and asphalt coats, wood, corroded metal, galvanized steel. For information about other substrates, please contact our tech department.

Standard concrete substrate conditions (no primer needed):

- Hardness: R₂₈ = 15 Mpa.



Certified quality, environmental and occupational health & safety management systems:
ISO 9001/14001 & OHSAS 18001.

HYPERDESMO® -S

- Humidity: W < 10%.
- Temperature: 5-35 °C.
- Relative humidity: < 85%.

Primer selection for special conditions and substrates:

Please refer to the **Primer Selection Table**.

APPLICATION PROCEDURE

Clean the substrate using a high pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, cured membranes must also be removed. Surface irregularities should also be filled with **HYPERSEAL®-25LM-S** or **HYPERSEAL®-EXPERT**.

Priming:

Apply the required primer following the guidelines above.

Mixing:

Use a low speed (300 rpm) mixer. Add SOLVENT-01 5-10% for application by spraying.

Application:

Apply with roller, brush or airless spraying (200-250 bar) in one or two coats. Do not exceed 48 hours between coats.

CONSUMPTION

Minimum total consumption: **1.5 kg/m²** in one or two coats.

CLEANING

Clean tools and equipment first with paper and then using SOLVENT-01. Rollers will not be re-usable.

PACKAGING

1 kg, 6 kg, 15 kg, 25 kg and 200 kg drums.

SHELF LIFE

Can be kept for 12 months minimum in the original unopened pails in dry places and at temperatures of 5-25 °C. Once opened, use as soon as possible.

SAFETY INFORMATION

Please refer to the Material Safety Data sheet as issued at the time of purchase.



Certified quality, environmental and occupational health & safety management systems:
ISO 9001/14001 & OHSAS 18001.

HYPERDESMO® -S

TECHNICAL SPECIFICATIONS

In liquid form (before application):

PROPERTY	UNITS	METHOD	SPECIFICATION
Viscosity (Brookfield)	cP	ASTM D2196-86, @ 25 °C	2000-4000
Specific weight	gr/cm ³	ASTM D1475 / DIN 53217 / ISO 2811, @ 20 °C	1.5

In cured form (after application):

PROPERTY	UNITS	METHOD	SPECIFICATION
Service temperature	°C	-	-40 to 80
Hardness	Shore A	ASTM D2240 / DIN 53505 / ISO R868	60
Tensile strength at break @ 23 °C	Kg/cm ² (N/mm ²)	ASTM D412 / EN-ISO-527-3	30 (3.0)
Elongation @ 23 °C	%	ASTM D412 / EN-ISO-527-3	> 800
Water vapor transmission	gr/m ² .hr	ASTM E96 (Water Method)	0.8
Water Absorption (7 days RT)	%	Internal Method	1
QUV Accelerated Weathering Test (4hr UV, @ 60 °C (UVB-Lamps) & 4hr COND @ 50 °C)	-	ASTM G53	passed (2000 hours)



Certified quality, environmental and occupational health & safety management systems:
ISO 9001/14001 & OHSAS 18001.